

Broadview Packaging Co., Ltd.

Block 49 & 50; No. 88 Haitian Road;
Hecheng Street; Gaoming District;
Foshan City; Guangdong;
PR China.

Technical Data Sheet For Green LDPE Grippie Bags

Product Description :

Green LDPE Grippie bags; 100% made of Braskems' Green LDPE SEB853_72 resin by extrusion process;

We are using Braskems' Green LDPE SEB853_72 resin which are of good optical properties.

Satisfy the EU Reach; RoHS & SML requirements;

Suitable for food & general packing application.

Storage conditions : 40°C to -18°C of good ventilation; cold storage packing to -18°C

General Properties :

Density : 0.923 gm/cm³

Peak Melting Temperature : 108°C

Tensil Strength :

Horizontal 26Mpa

Vertical 1.2Kgs

Heat Seal Strength : 3.4Kgs.

Strength at Yield MD : 1500psi

Strength at Yield TD : 1500psi

Strength at Break MD : 2800psi

Strength at Break TD : 2200psi

Elongation At Break MD : 220%

Elongation At Break TD : 450%

Heat Seal Strength : 3.4Kgs.

Gloss (45 Degree) : 70

Haze : 5.4%

Complied Cert.s & Reports :

Braskems' Green LDPE SEB853_72 resin – TDS & MSDS

Broadview ISO; GMP Certificates & SML report.

